Application No.: 10/583,895
 Docket No.: 4555-0111PUS1

 Amendment filed with RCE
 Page 2 of 6

## AMENDMENTS TO THE CLAIMS

- 1. (Currently Amended) A cleansing polyester fabric, which comprises
- (i) a <u>warp consisting of a false twist yarn consisting of polyester multifilament</u> eensisting of having ultra fine yarns (monofilament fibrils) of 0.001 to 0.1 deniers er-its-false twist yarn as warp and
- (ii) a weft consisting of a false twisted yarn consisting of the polyester multifilament consisting of ultra yarns (monofilament fibrils) of 0.001 to 0.1 deniers and a high shrinkage polyester multifilament with 10~50% of shrinkage rate in boiling water as—weft, wherein the fabric weave is a plain weave or twill weave, and the fabric satisfies the following properties:

Sum of warp density and weft density: 220-320 yarns/inch

Thickness of the fabric: less than 0.3 mm

Weight of the fabric 70-180 g/m<sup>2</sup>.

- 2-3. (Canceled)
- 4. (Original) The cleansing polyester fabric of claim 1, wherein the ultra fine yarns (monofilament fibrils) of the warp and weft are cross-linked to one another, being distributed and spread, as the surface of the fabric is treated by a friction material.
  - 5-10. (Canceled)
- 11. (Previously Presented) The cleansing polyester fabric of claim 1, wherein the plain weave or twill weave has a short-repeat interval of at least one selected from the group consisting of 2UP 1DOWN, 1UP 2DOWN, 2UP 2DOWN, 3UP 1DOWN and 1UP 3DOWN.
- 12. (Previously Presented) The cleansing polyester fabric of claim 1, wherein the warp density is 150-210 yarns/inch and the weft density is 70-110 yarns/inch.